

## KEMPEROL AC Speed+ Sealing



### Uses

- As seal in conjunction with KEMPEROL 165 fleece for making connections
- Suitable for outdoor applications
- For new buildings and repair work
- Can be applied to practically any substrate

### Features

- Rapid-curing
- Cold applied
- Water vapour permeable
- Crack bridging
- Root resistant according to FLL-testing
- Can be walked on for maintenance
- Solvent-free
- UV resistant
- 2-component
- Light-stable
- Workable of ambient temperatures of up to -5 °C
- CE marking
- Resin base: PMMA
- Alkali resistant

### Usage guide

depending on the nature of the substrate: at least 2,5 kg/m<sup>2</sup> depending on the layer thickness (see Technical Information TI 03 - Layer thicknesses according to regulations).

### Pack sizes

10 kg container (component A) in combination with KEMPEROL CP catalyst powder (component B), refer to the Curing Table for recommended quantities.

### Shelf Life

Can be stored cool, frost-free, dry and unopened. Best before: see container label.

### Properties

Form	comp. A liquid
	Comp. B powder
Standard colour	Traffic grey
	Anthracite
Workability time*	approx. 15 min
Rainproof after*	approx. 35 min
Can be walked on after*	approx. 35 min
Cured after*	approx. see curing table
Further coating after*	approx. 60 min

\* Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

### Test results according to ETAG 005

Water vapour diffusion factor $\mu$	~ 6600
Resistance to wind loads	1,6 N/mm <sup>2</sup>
External fire performance	B <sub>ROOF(t1)</sub> **
Reaction to fire	E ***
Statement to dangerous substances	does not contain any
Working life	W3
Climatic zones	M and S
Imposed loads	P1 to P4
Roof slope	S1 to S4
Lowest surface temperature	TL4
Highest surface temperature	TH4

\*\* Classification in accordance with EN 13501-5

\*\*\* Classification in accordance with EN 13501-1.

### Curing

Hardening takes place with KEMPEROL CP catalyst powder. The quantity added depends on the temperature.

**Table for 10 kg  
KEMPEROL AC Speed+ Waterproofing**

Temperature [°C]	KEMP. CP cat. powder - quantity [g]	Pot life in container [min]	Rainproof / surface cured [min]
-5°C	400	60 min	90 min
0°C	400	45 min	80 min
+5°C	400	35 min	70 min
+10°C	400	30 min	60 min
+20°C	200	20 min	35 min
+30°C	100	20 min	30 min

## Application

### Preparing the substrate

The substrate must be dry (in concrete, the residual moisture in the upper 2 cm must be < 5 %), sound and free from any material that would hinder adhesion.

A primer is not required for all substrates. In general, the priming recommendation for KEMPEROL AC Speed should be considered.

When executed, the surface temperature must be 3 K above the dew point. If the dew point is undershot, a moisture film, which has a separating effect, can form on the surface to be processed (see Technical Information TI 16).

### Preparation

If the ambient temperature is 10°C or lower, it is recommended that you store and mix the components at room temperature.

At temperatures above +25°C, protect the material against direct sunlight.

### Mixing

KEMPEROL AC Speed+ Waterproofing may only with KEMPEROL CP catalyst powder may be used. The quantity of the catalyst powder must be adapted to the respective material temperature (see Table Hardening

### Use

The Waterproofing is produced by mixing KEMPEROL CP catalyst powder and KEMPEROL AC Speed+ Waterproofing and KEMPEROL 165 fleece.

Connections to door and window elements etc. with a height of <15 cm (from upper edge of coating) should have at least 5 cm of overlap. Connections and joints to third party products have to be produced with an overlap of at least 10 cm.

Avoid applying the material beyond the area covered by the fleece.

Before the next coat of KEMPERDUR MT mineral tile adhesive can be applied a bonding coat is necessary.

Interruptions of more than 1 days: Clean the working area with KEMCO MEK Cleaning Agent.

## Note

Please consider the following technical information:

- TI 21 - substrate preparation
- TI 22 - Application of KEMPEROL/KEMPERDUR AC products
- TI 33 - processing of KEMPEROL AC Speed / AC Speed+ sealings at temperatures below +5°C
- TI 34 - Correct masking of the surface to be treated with KEMPEROL

## Important notes

When applying KEMPEROL AC Speed+ Waterproofing explosion protection for working equipment is necessary.

The applicable "rules of application" in its current version as well as the "standard rules of technology" and the state of the art for the respective task apply during waterproofing production. For chemical resistance, see the Chemical Resistance List A-Z.

The safety data sheets, identification of the containers, hazard statements and the safety recommendations on the containers must be observed during transportation, storage and application. The BG-Chemie technical data sheets must be observed during application.

Multi-component polyurethane, polyester, epoxy and methyl methacrylate resins react under heat development. After mixing the components, the product must not remain in the mixing container for longer than the workability time. Non observance may cause heat and smoke development and may, in extreme cases, even result in a fire.

## Disposal

Liquid	EAK 08 04 09
cured	EAK 08 04 10

## GISCODE

RMA10

## General information

Changes to the colour caused by weather conditions or UV rays do not influence the technical parameters. The times given above are reduced with higher and increased with lower ambient and substrate temperatures.

No substances of other systems may be mixed into the products of the KEMPER SYSTEM.

Only for commercial use.

Our technical data sheets / technical information and application instructions reflect the current level of knowledge in our company and the experience with our products. In each case, the new edition su-

persedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practise. The latest version can be retrieved from the KEMPER SYSTEM Login section. When using our products, a detailed, object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We are liable only for our products being free from faults, and this only if our relevant product has been used and applied according to the instructions in our technical data sheets. Correct application of our products therefore falls entirely within the scope of liability and responsibility of the user (contractor). Our products are sold exclusively on the bases of our conditions of sale and delivery.

Issued: Vellmar, 2021-03-15