

## KEMPEROL 2K-PUR Speedshot



### Uses

- To speed up the reaction of KEMPEROL 2K-PUR waterproofing

### Features

- Shortens the setting process of KEMPEROL 2K-PUR waterproofing

### Pack sizes

0,9 kg in a plastic bottle with a measuring chamber

### Shelf Life

Can be stored cool, frost-free, dry and unopened. Best before: see container label.

### Usage guide

Specifications refer to a quantity of 1 kg KEMPEROL 2K-PUR waterproofing

Temperature*** [°C]		10 ml	20 ml	30 ml
5°C	V*	21 min	15 min	12 min
	W**	6.5 h	5.5 h	5 h
10°C	V*	20 min	12 min	9 min
	W**	5.5 h	4.5 h	3.5 h
15°C	V*	16 min	10 min	7 min
	W**	5 h	3.5 h	3 h
20°C	V*	11 min	7 min	5 min
	W**	3.5 h	2.5 h	2 h

Temperature*** [°C]		10 ml	20 ml	30 ml
25°C	V*	10 min	6 min	-
	W**	3 h	2 h	-
30°C	V*	7 min	-	-
	W**	2 h	-	-

\* Working time

\*\* Further coating after

\*\*\* Temperature of KEMPEROL 2K-PUR waterproofing

Specifications refer to a quantity of 2.5 kg KEMPEROL 2K-PUR waterproofing

Temperature*** [°C]		1 Shot (25 ml)	2 Shot (50 ml)	3 Shot (75 ml)
5°C	V*	21 min	15 min	12 min
	W**	6.5 h	5.5 h	5 h
10°C	V*	20 min	12 min	9 min
	W**	5.5 h	4.5 h	3.5 h
15°C	V*	16 min	10 min	7 min
	W**	5 h	3.5 h	3 h
20°C	V*	11 min	7 min	5 min
	W**	3.5 h	2.5 h	2 h
25°C	V*	10 min	6 min	-
	W**	3 h	2 h	-
30°C	V*	7 min	-	-
	W**	2 h	-	-

\* Working time

\*\* Further coating after

\*\*\* Temperature of KEMPEROL 2K-PUR waterproofing

Specifications refer to a quantity of 12.5 kg KEMPEROL 2K-PUR waterproofing

Temperature*** [°C]		1 Shot (25 ml)	2 Shot (50 ml)	3 Shot (75 ml)
5°C	V*	-	-	22 min
	W**	-	-	4.5 h
10°C	V*	-	-	22 min
	W**	-	-	4.5 h
20°C	V*	20 min	18 min	-
	W**	7 h	6 h	-

\* Working time

\*\* Further coating after

\*\*\* Temperature of KEMPEROL 2K-PUR waterproofing

### Properties

Form Liquid

\* Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

---

## Application

### Preparation

To add the correct dosage of KEMPEROL 2K-PUR Speedshot first screw the blue cap to the measuring chamber of the bottle. Then squeeze the bottle repeatedly until the dosage chamber has filled up to the 25ml line. 25 ml is one shot.

If the ambient temperature is 10°C or lower, it is recommended that you store and mix the components at room temperature.

### Sachet

KEMPEROL 2K-PUR waterproofing Mix according to instructions in a kneading bag and then perform the re-potting. KEMPEROL 2K-PUR Speedshot mix with a stirring rod or a slowly running stirrer, streak-free into the finished seal KEMPEROL 2K-PUR . Mixing time is approx 1 minute.

### PPE

Personal protective equipment should be worn. We recommend a hand protection and skin protection plan adapted to the workplace. Clean the tools immediately after use with KEMCO MEK Cleaning Agent.

---

## Important notes

The safety data sheets, identification of the containers, hazard statements and the safety recommendations on the containers must be observed during transportation, storage and application. The BG-Chemie technical data sheets must be observed during application.

Do not allow to enter waters, drains or to penetrate the ground.

---

## Disposal

Liquid                      EWC 07 02 04

---

---

## General information

No substances of other systems may be mixed into the products of the KEMPER SYSTEM.

Only for commercial use.

Our technical data sheets / technical information and application instructions reflect the current level of knowledge in our company and the experience with our products. In each case, the new edition supersedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practise. The latest version can be retrieved from the KEMPER SYSTEM Login section. When using our products, a detailed, object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We are liable only for our products being free from faults, and this

only if our relevant product has been used and applied according to the instructions in our technical data sheets. Correct application of our products therefore falls entirely within the scope of liability and responsibility of the user (contractor). Our products are sold exclusively on the bases of our conditions of sale and delivery.

Issued: Vellmar, 2021-03-15